



DELTA SYNT MEDIA

Filtering stage: I & II
Filtration class: CEN-EN779 G & F
Media: Polyester
Market: HVAC | Food/Beverage | Industrial



Technical Details

Model	Grade	Weight Gr/m ²	Thickness mm	Length m	Initial Pressure Drop Pa	Final Pressure Drop Pa	Efficiency %	Flame Test
DR100	G3	100	5	40	21	250	81,74	F1/B2
DR130	G3	130	7	40	31	250	89,1	F1
DR150	G4	160	10	40	45	250	90,1	F1
DR190B	G3	176	18	20	47	250	83	F1/B2
DR210B	G4	20	20	20	55	250	90,4	F1/B2
DR250B	G4	250	16	20	47	250	92,1	F1/B2
DR280	G4	300	22	20	71	250	93,5	F1/B2
DR400	G4	350	20	20	61	250	94,8	F1/M1
DR50/400	G4	406	50	20	52	250	91,5	F1
DR500FH	F5	512	20	20	30	450	96,7	F1/B2
DR600	F5	600	22	20	30	450	97,5	F1/B2
Max. Temperature					80°C			
Width					2 m			

Contact Details

Delta Filtration, Kilmallock Business Park, Kilmallock, Co. Limerick, Ireland

Tel : +353 63 98829 | Fax : +353 63 98830 | E-mail : info@deltafiltration.com | Web : www.deltafiltration.com